

Angle Bar

Standard Sectional Dimension		Unit Weight
A x A	Thickness t (mm)	Kg/m
20 x 20	2.5	0.74
	3	0.86
25 x 25	2.5	0.95
	3	1.12
	4	1.5
	5	1.76
	6	2.24
30 x 30	2.5	1.14
	3	1.36
	4	1.76
	5	2.16
	6	2.74
38 x 38	2.5	1.46
	3	1.74
	4	2.26
	5	2.79
	6	3.50
50 x 50	3	2.33
	4	3.06
	5	3.77
	6	4.43
	8	5.78
60 x 60	5	4.55
	6	5.42
63 x 63	5	4.75
	6	5.71
65 x 65	5	5.00
	6	5.91
	8	7.66
	9	8.55
70 x 70	6	6.38
	7	7.38
	8	8.43
75 x 75	5	5.76
	6	6.85
	8	9.03
	9	9.96
	12	13.00
80 x 80	6	7.32
	8	9.66
	9	10.70
90 x 90	6	8.28
	7	9.59
	8	10.90
	9	12.20
	10	13.30

100 x 100	6	9.20
	7	10.70
	8	12.20
	9	13.50
	10	15.00
	12	17.80
125 x 125	10	19.09
	12	22.67
150 x 150	10	23.00
	12	27.30
	15	33.80
200 x 200	15	45.30
	20	59.90

Thickness Tolerance  $\pm 10\%$

*HC*